

REPORT DOCUMENTATION PAGE

Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing this collection of information. Send comments regarding this burden estimate or this burden to Department of Defense, Washington Headquarters Services, Directorate for Information Operations and Report 4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to any penalty for not providing any information if it does not contain the information requested. PLEASE DO NOT RETURN YOUR FORM TO THE ABOVE ADDRESS.

AFRL-SR-BL-TR-00-

ntaining the
or reducing
A 22202-
y a currently

1. REPORT DATE (DD-MM-YYYY) 26-08-2000		2. REPORT TYPE Final Technical and Progress		01-03-1998-28-02-2000	
4. TITLE AND SUBTITLE (DURIP98/99) Slow Positron Beam for Materials and Surface Characterization				5a. CONTRACT NUMBER	
				5b. GRANT NUMBER F49620-98-1-0309	
				5c. PROGRAM ELEMENT NUMBER	
6. AUTHOR(S) Yanching Jean (PI) Thomas C. Sandreczki (co-PI)				5d. PROJECT NUMBER	
				5e. TASK NUMBER	
				5f. WORK UNIT NUMBER	
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) University of Missouri-Kansas City, Office of Res. Admin. 354 AC, 5100 Rockhill Rd. Kansas City, MO 64110				8. PERFORMING ORGANIZATION REPORT NUMBER	
9. SPONSORING / MONITORING AGENCY NAME(S) AND ADDRESS(ES) AFOSR/NL 801 N. Randolph St. Rm. 732 Arlington, VA 22203-1977				10. SPONSOR/MONITOR'S ACRONYM(S) AFOSR/Charles Lee	
				11. SPONSOR/MONITOR'S REPORT NUMBER(S)	
12. DISTRIBUTION / AVAILABILITY STATEMENT APPROVED FOR PUBLIC RELEASE: DISTRIBUTION UNLIMITED A newly built slow positron has been available for surface and materials characterization with high intensity and good resolution. The scientific results have been reported in four refereed publications: Appl. Surf. Sci. 149(1999)116; Radia. Phys. Chem. 58(2000)645; Radia. Phys. Chem. 58(2000)571; Radia. Phys. Chem. 58(2000)639.					
13. SUPPLEMENTARY NOTES Two reprints in ACS conferences: Polym. Mat. Sci. 83(2000)122 and 83(2000)334.					
14. ABSTRACT A variable, mono-energetic slow positron beam (0-30 keV) coupled with Doppler broadening of annihilation radiation and positron lifetime measurements has been constructed at the University of Missouri-Kansas City. The beam is ideal for surface and materials characterization of defects of polymeric and coating materials in the range of sub-nanometer on the surface to a few μm in the bulk. This instrument becomes one of five slow positron beams currently available in the US for research on sub-nanometer defects and for training students and scientists in defense-related research. The performance of the beam, the counting rate and the resolution, is one of the best in the world.					
15. SUBJECT TERMS polymers, materials, coatings, sub-nanometer defects					
16. SECURITY CLASSIFICATION OF:			17. LIMITATION OF ABSTRACT	18. NUMBER OF PAGES 3	19a. NAME OF RESPONSIBLE PERSON Yanching Jean
a. REPORT Unclass	b. ABSTRACT Unclass	c. THIS PAGE Unclass			19b. TELEPHONE NUMBER (include area code) 816-235-2295

Standard Form 298 (Rev. 8-98)
Prescribed by ANSI Std. Z39.18

A. Summary of the Progress and Important Accomplishments:

We have installed a slow positron beam with a capability of varying energy from 0 to 30 keV at the University of Missouri-Kansas City. The beam is designed for characterization of sub-nanometer defects, such as free volumes and holes at the atomic and molecular levels by monitoring the nature of positron-electron annihilation signals. This spectrometer is able to detect the early stage of coating degradation within hours of accelerated UV irradiation. It is one of five slow positron beams available for surface and materials characterization in the US.

Based on this research, a portable, field-based positron spectrometer for accelerated testing of coating degradation, such as a NDE instrument may become feasible in the future.

(1) The performance of the slow positron beam is one of the best among the existing slow positron beams in the world with the following specifications:

- a. Flux: 1×10^5 slow positrons per second at the sample by using 50 mCi of Na-22 positron source.
- b. The beam spot is on the order of 5 mm diameter.
- c. UHV chamber condition down to 1×10^{-10} torr.
- d. Measuring Doppler broadening of annihilation radiation for defect parameter.
- e. Positron lifetime measurements.
- f. The beam operation is automatically controlled by a Pentium III PC.

Fig. 1 shows the schematic diagram of the constructed beam.




Figure 1. A schematic diagram of the slow positron beam at the University of Missouri-Kansas City. A: 50 mCi ^{22}Na positron source, B: W-mesh moderator, C: magnetic field (75G) coils, D: ExB filter, E: positron accelerator, F: correcting magnets, G: gas inlet, H: positron bunching system for PAL, I: turbo molecular pump, J: samples, K: sample manipulator, L: cryo pump, M: Ge solid state detector, N: lifetime detector.

(2) The built beam has been used to perform research projects in conjunction with grants of AFOSR (F49620-98-1-0162) and NSF (CMS98-12717). Main scientific results obtained from this beam are:

- a. The weathering resulting from controlled UV, xenon light, and humidity all reduce the defect (sub-nanometer) size and concentrations. The reduction of free-volume and holes induces the degradation and shortens the durability of coatings.
- b. The defect microstructure of polymers and coatings near the surface is very different from the bulk. Inhomogeneous chemical and physical profiles were determined. This gives us an important guide to search for the improvement of coating durability.
- c. Degradation of coatings is largely increased by a factor of about ten as the UV wavelength is shortened from 340 to 313 nm.
- d. UV degradation is through the photo-oxidation mechanism, which is propagated by the reaction between oxygen and polymer chains, the formation of free radicals, and the increase of crosslinking density.

B. These results have been published in the following refereed papers that acknowledge the AFOSR support:

1. "Free Volumes and Holes Near the Polymer Surface Studied by Positron Annihilation," *Appl. Surf. Sci.* 149(1999)116-124.
H. Cao, J.-P. Yuan, C.S. Sundar, Y.C. Jean, R. Suzuki, T. Ohdaira, and B. Nielsen.
2. "Application of Slow Positrons to Coating Degradation," *Rad.Phys.Chem.* 58(2000)645-648.
H. Cao, R. Zhang, H.M. Chen, P. Mallon, C.-M. Huang, Y. He, T.C. Sandreczki, Y.C. Jean, B. Nielsen, T. Friessnegg, R. Suzuki, T. Ohdaira.
3. "Positron Annihilation Studies of Chromophore-Doped Polymers," *Rad.Phys.Chem.* 58(2000)571-574.
C.-M. Huang, J.-P. Yuan, H. Cao, R. Zhang, Y.C. Jean, R. Suzuki, T. Ohdaira, B. Nielsen.
4. "Development of Positron Annihilation Spectroscopy for Accelerated Weathering of Protective Polymer Coating," *Rad.Phys.Chem.* 58(2000)639-644.
R. Zhang, H. Cao, H.M. Chen, P. Mallon, Y. He, T.C. Sandreczki, R.J. Richardson, Y.C. Jean, B. Nielsen, R. Suzuki, T. Ohdaira.

Two additional papers (un-refereed) have been published:

5. "Photo-degradation of Polymeric Coatings Studies by Positron Annihilation Spectroscopy," *ACS Polym. Mate. Sci. & Eng.* 83(2000)334-335.
Y.C. Jean, R. Zhang, H. Chen, P. Mallon, J. Zhang, Y. Li, C-M. Huang, T.C. Sandreczki, J. Richardson, R. Suzuki, T. Ohdaira, and B. Nielsen.

6. "Positron Annihilation Spectroscopy as a Novel Accelerated Method for UV Degradation of Polymers," *ACS Polym. Mater. Sci. & Eng.* 83(2000)122-123.
Y.C. Jean, Y. Li, P. Mallon, R. Zhang, H. Chen, P. Mallon, J. Zhang, C-M. Huang,
T.C. Sandreczki, Y.Y. Huang.